



DIN 6921 - DIN 7500

Cold-formed steel parts according to drawing.

Materials: C23B carbonitrided

Core hardness: 320–380 HV10

Surface hardness: min 450 HV03

